



IMPORTADORA

**CHIRIBOGA  
& JARA S.A.**

Urb. Sta Adriana Mz 3 Sl 7, Av J.T. Marengo Km 5 1/2, Guayaquil-Ecuador

GYE: (593-4) 6005004 - (593-4) 6005005

GYE: (593-4) 3082583

[www.chiribogayjara.com](http://www.chiribogayjara.com)

WR3

<b>Tube</b>	Oil resistant synthetic rubber
<b>Reinforcement</b>	Two textile braids
<b>Cover</b>	Abrasion and weather resistant synthetic rubber
<b>Application</b>	Used to convey mineral oil based hydraulic oil, oil and water emulsion and aqueous glycol solutions
<b>Temperature</b>	-40°C to +100°C
<b>Safety Factor</b>	4:1

I.D.		WORKING PRESSURE		TEST PRESSURE		BURST PRESSURE		BEND RADIUS	WEIGHT (APPROX)
DN	INCH	BAR	PSI	BAR	PSI	BAR	PSI	mm	Kg/m
12	1/2	70	1015	140	2030	280	4060	125	0.40
19	3/4	52	750	104	1508	208	3016	150	0.61
25	1	39	565.5	78	1131	156	2262	205	0.91

1 Bar= 14.5 PSI