



IMPORTADORA

**CHIRIBOGA**  
& JARA S.A.

Urb. Sta Adriana Mz 3 Sl 7, Av J.T. Marengo Km 5 1/2, Guayaquil-Ecuador

**GYE:** (593-4) 6005004 - (593-4) 6005005

**GYE:** (593-4) 3082583

www.chiribogayjara.com (<http://chiribogayjara.com>)

**W WINFLEX®** WR7-06N - SAE 100R7-1/4" - MWP 155

**WR7 (NON CONDUCTIVE)**

- Tube:** Nylon 11
- Reinforcement:** One layer of synthetic fiber braid
- Cover:** Non-Conductive Polyurethane
- Application:** Compatible w/most hydraulic fluids, designed for use where electric shock hazards exist. Max leakage is 50 Micro Amperes per ft. @ 75KV per ft. for 5 minutes.
- Temperature:** -40°C to +93°C
- Safety Factor:** 4:1

I.D		WORKING PRESSURE		TEST PRESSURE		BURST PRESSURE		BEND RADIUS	WEIGHT (APPROX)
DN	INCH	BAR	PSI	BAR	PSI	BAR	PSI	mm	Kg/m
6	1/4	255	3260	510	6520	1020	13040	100	0.090
10	3/8	155	2250	310	4500	620	9000	125	0.155
13	1/2	140	2030	280	4060	560	8120	180	0.224